



CHR[®] TAPE 

CHR[®] 2275

Specialized for Extreme Conditions

Extruded, Oriented, High Modulus PTFE Pressure Sensitive Adhesive Tape

CHR[®] 2275-2 is manufactured from extruded, oriented, high-modulus PTFE film coated with high-temperature silicone adhesive.

Features/Benefits



The oriented PTFE film used to make the CHR[®] 2275-2 adhesive tape is processed to provide high tensile strength and exceptional abrasion resistance while maintaining the superior release properties offered by PTFE. The specially formulated, high-temperature silicone adhesive has excellent adhesion both to the surface to which the tape is being applied as well as to its own backing when wrapped on itself to assure that the tape stays bonded during the application. CHR[®] 2275-2 removes cleanly after use and is pigmented to facilitate visual inspection during use.

Availability

Factory stock is in master log form 33 m x 254 mm wide. Rolls can be slit in widths ranging from 12.7 mm to 254 mm.

Applications

CHR[®] 2275-2 is designed to be used as a high-temperature “roller wrap” tape in the production of polyethylene/polypropylene laminates. During this process, the plastic is extruded onto a substrate as it passes through a number of rolls. The tape is wrapped around the rolls to protect the exposed ends of the rollers from the molten plastic, thus preventing build-up of the plastic on the roll surface. The high-temperature capabilities and exceptional durability of 2275-2 enables the tape to be used for long continuous laminating production runs. CHR[®] 2275-2 can also be used to fabricate belts used in laminating applications as well as other applications that require the temperature and release properties of the tape.




SAINT-GOBAIN

CHR® 2275 Properties

Performance tests are run using standard test procedures.
The values presented are typical values and should not be used for specification purposes.

Product Number	2275-2
Backing Material	Film-PTFE
Adhesive Type	Silicone
Total Thickness (mm)	0.107
Backing Thickness (mm)	0.058
Adhesive Thickness (mm)	0.048
Adhesion to Steel (N/cm)	4.4
Tensile Strength (N/cm)	79
Dielectric Strength (volts)	11,000
Elongation (% at break)	110
Operating Temperature (°C)	-73 to +260
Colour	Rust

CHR® is a registered trademark.



Saint-Gobain

AMERICAS

Tel: (800) 962-2666
(518) 686-7301

EUROPE

Tel: +44 (0) 1706-746900

ASIA

Tel: (886) 2-2503-4201

www.foamsandtapes.saint-gobain.com

AMERICAS: 14 McCaffrey Street, Hoosick Falls, NY 12090, USA

EUROPE: Bay 3 Transpennine Industrial Estate, Gorrels Way, Rochdale, OL11 2PX, UK

ASIA: Room 302,3F-1, 147 Jianguo North Road, Section 2, Taipei, Taiwan, 104

The data and details in this document were correct and up-to-date at the time of printing and are intended to provide information on our products and their possible applications. It is the user's responsibility to obtain the latest version of the product data sheet. This data sheet is not a specification and does not assure specific product characteristics or make reference to the suitability of the product for a specific application. Because Saint-Gobain cannot anticipate or control every application, we strongly recommend testing of this product under individual application conditions. The application, use and conversion of this product are the user's responsibility.

Limited Warranty: For a period of 6 months from the date of first sale, Saint-Gobain Performance Plastics warrants this product(s) to be free from defects in manufacturing. Our only obligation will be to provide replacement product for any portion proving defective, or at our option, to refund the purchase price thereof. User assumes all other risks, if any, including the risk of injury, loss or damage, whether direct or consequential, arising out of the use, misuse or inability to use this product(s).

SAINT-GOBAIN PERFORMANCE PLASTICS DISCLAIMS ANY AND ALL OTHER WARRANTIES, EXPRESSED OR IMPLIED, INCLUDING THE IMPLIED WARRANTIES OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE.

NOTE: Saint-Gobain Performance Plastics Corporation does not assume any responsibility or liability for any advice furnished by it, or for the performance or results of any installation or use of the product(s) or of any final product into which the product(s) may be incorporated by the purchaser and/or user. The purchaser and/or user should perform their own tests to determine the suitability and fitness of the product(s) for the particular purpose desired in any given situation.

2275-2-EN-CHREU-RR-1605

©2016 Saint-Gobain Performance Plastics