

Closed-cell PVC foam

Siliconized paper liner

Pressure-sensitive acrylic adhesive

**NORSEAL**®

**C Foam**

Providing protection in your harshest environment

## Firm, Closed-Cell, Automotive Polyvinyl Chloride Foam

Saint-Gobain NORSEAL® PVC C Foam is a closed-cell PVC foam sealant with or without a pressure-sensitive adhesive on one side. Its high-density structure dampens vibration and offers good abrasion resistance for severe automotive applications.

The NORSEAL C Foam series is specially designed to provide the following features:

- Dimensionally stable under compression
- Good abrasion resistance
- Flame resistant to meet FMVSS 302
- Resistant to weather, fungi, and oxidation
- Low water absorption for long sealing life

### OEM Approvals

Chrysler Specification Number: MSAY500 (Type 5)

Ford Specification Number: ESB-M4G70-A

General Motors Specification Number: GMW15473 (Type V- Class 2)

### Available Sizes

Standard thickness: .063, .125, .188, .25, .375 and .50 in. (1.6, 3.2, 4.8, 6.4, 9.5 and 12.7 mm)

Master roll size: 56 in. (1422 mm) width. Length varies with thickness.

Special thickness and roll sizes also available.



### Applications

- Instrumentation panel
- HVAC
- Sunroofs
- Vibration dampening
- Gas strap

  
**SAINT-GOBAIN**

## NORSEAL® C Foam – Properties

Performance tests are run using standard test procedures. The values presented are typical values and should not be used for specification purposes.

Property	Test Method	Value or Rating
Density lbs./cu. ft. (kg/m <sup>3</sup> )	ASTM D-1667	15 (240)
Hardness: Shore oo	ASTM D-2240	52
Force to Compress: psi (kPa)*	ASTM D-1667	14 (94)
Compression Deflection: psi (kPa)*	ASTM D-1667	9 (64)
Compression Set: % lost fr. orig. ht.*	NTP-37	5
Water Absorption (% by volume)*	NTP-35	2
90° Peel Adhesion: oz./in (N/m) 15 min. dwell	PSTC-2	23 (251)
Elongation %	ASTM D-412 Die A	160
Tensile: psi (kPa)	ASTM D-412 Die A	115 (790)
Tear Strength, pli (kM/m)	ASTM D624 Die C	18 (3.7)
Flammability Resistance	FMVSS 302	Pass
Foam Color	–	Black

\* Based on 30% compression  
NTP: Internal Test Procedure

### Options (subject to minimum order requirements)

Adhesive base: No adhesive, available upon request.

Liner: Permanent PET film and other weight paper liners available upon request.

### Important Instructions

- Because Saint-Gobain cannot anticipate or control every potential application, we strongly recommend testing of this product under individual application conditions prior to commercial use. The product contains plasticizer, which may adversely affect some plastics.
- Surfaces must be clean and free of oil, grease, moisture, dust and dirt. Isopropyl alcohol is good for cleaning the surface. Do not remove liner until tape is in proper position. Avoid touching adhesive surface before application. The adhesive is intended for positioning during the assembly process. The foam tape is secured in the joint by compression of the adjacent substrates.
- The application temperature should be between 40°F and 125°F (4°C to 52°C). It is not recommended to apply these sealants at temperatures below 40°F (16°C), as the adhesive does not flow in this condition and can result in poor bonding. Recommended service temperature is between -15°F to 160°F (-26°C to 71°C).

### Shelf Life

6 months after the date of sale when stored in original packaging at temperatures up to 70°F (21°C) and 50% relative humidity.

NORSEAL® is a trademark of Saint-Gobain Performance Plastics.

## NORSEAL® C Foam – Standard Roll Sizes

Product No.	Thickness in. (mm)	Length ft. (m)
C02	.063 (1.6)	150 (45.7)
C04	.125 (3.2)	75 (22.9)
C06	.188 (4.8)	50 (15.2)
C08	.25 (6.4)	50 (15.2)
C12	.375 (9.5)	25 (7.6)
C16	.50 (12.7)	25 (7.6)

3" I.D. cardboard cores standard



**Saint-Gobain  
Performance Plastics**

One Sealants Park  
Granville, NY 12832  
Tel: (800) 724-0883  
(518) 642-2200  
Fax: (518) 642-2793

[foams@saint-gobain.com](mailto:foams@saint-gobain.com)  
[www.foams.saint-gobain.com](http://www.foams.saint-gobain.com)

The data and details in this document were correct and up-to-date at the time of printing and are intended to provide information on our products and their possible applications. It is the user's responsibility to obtain the latest version of the product data sheet. This data sheet is not a specification and does not assure specific product characteristics or make reference to the suitability of the product for a specific application. Because Saint-Gobain cannot anticipate or control every application, we strongly recommend testing of this product under individual application conditions. The application, use and conversion of this product are the user's responsibility.

Limited Warranty: For a period of 6 months from the date of first sale, Saint-Gobain Performance Plastics warrants this product(s) to be free from defects in manufacturing. Our only obligation will be to provide replacement product for any portion proving defective, or at our option, to refund the purchase price thereof. User assumes all other risks, if any, including the risk of injury, loss or damage, whether direct or consequential, arising out of the use, misuse or inability to use this product(s).

SAINT-GOBAIN PERFORMANCE PLASTICS DISCLAIMS ANY AND ALL OTHER WARRANTIES, EXPRESSED OR IMPLIED, INCLUDING THE IMPLIED WARRANTIES OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE.

NOTE: Saint-Gobain Performance Plastics Corporation does not assume any responsibility or liability for any advice furnished by it, or for the performance or results of any installation or use of the product(s) or of any final product into which the product(s) may be incorporated by the purchaser and/or user. The purchaser and/or user should perform their own tests to determine the suitability and fitness of the product(s) for the particular purpose desired in any given situation.

SPPE-5368-0716-SGCS

©2016 Saint-Gobain Performance Plastics