



CHR<sup>®</sup> TAPE 

CHR<sup>®</sup> 2302

Specialized for Extreme Conditions

## UHMW Pressure Sensitive Adhesive Tape

CHR<sup>®</sup> 2302 is manufactured from UHMW (Ultra High Molecular Weight) polyolefin film coated with acrylic adhesive.

### Features/Benefits

CHR<sup>®</sup> 2302 exhibits excellent abrasion resistance and a low coefficient of friction, making it an excellent protection for surfaces or bearings that experience heavy wear. It is more economical than PTFE tapes. The high-temperature, high-tack acrylic adhesive adheres readily to most dry, clean surfaces, firmly anchoring the product in place.

### Availability

Factory stock for 2302 is in master log form 33 m x 889 mm. Rolls can be slit in widths ranging from 6.35 mm to 889 mm. The product is supplied with a blue poly-film inter-liner, which protects the adhesive, facilitates die cutting, and peels off easily. Brown paper is also available as a custom product.

### Applications

CHR<sup>®</sup> 2302 can be used to provide an abrasion-resistant, anti-stick, anti-friction surface at temperatures up to 107 °C. It is frequently used to line chutes and conveyors. The product is often applied to guide rails to reduce noise levels in glass bottling plants. This tape is also used to replace desk drawer bearings, and to provide silky smooth, friction free drawer movement.



  
SAINT-GOBAIN

## CHR® 2302 Properties

Performance tests are run using standard test procedures.  
The values presented are typical values and should not be used for specification purposes.

Product Number	2302-3R	2302-5R	2302-10R	2302-20R
Backing Material	Film-UHMW	Film-UHMW	Film-UHMW	Film-UHMW
Adhesive Type	Acrylic	Acrylic	Acrylic	Acrylic
Total Thickness (mm)	0.114	0.165	0.292	0.546
Backing Thickness (mm)	0.076	0.127	0.254	0.508
Adhesive Thickness (mm)	0.038	0.038	0.038	0.038
Adhesion to Steel (N/cm)	3.8	4.9	5.5	5.5
Tensile Strength (N/cm)	35	70	140	254
Elongation (% at break)	300	350	425	500
Operating Temperature (°C)	-40 to +107	-40 to +107	-40 to +107	-40 to +107
Colour	Natural	Natural	Natural	Natural

CHR® is a registered trademark.



### Saint-Gobain

AMERICAS  
Tel: (800) 962-2666  
(518) 686-7301

EUROPE  
Tel: +44 (0) 1706-746900

ASIA  
Tel: (886) 2-2503-4201

[www.foamsandtapes.saint-gobain.com](http://www.foamsandtapes.saint-gobain.com)

AMERICAS: 14 McCaffrey Street, Hoosick Falls, NY 12090, USA

EUROPE: Bay 3 Transpennine Industrial Estate, Gorrels Way, Rochdale, OL11 2PX, UK

ASIA: Room 302,3F-1, 147 Jianguo North Road, Section 2, Taipei, Taiwan, 104

The data and details in this document were correct and up-to-date at the time of printing and are intended to provide information on our products and their possible applications. It is the user's responsibility to obtain the latest version of the product data sheet. This data sheet is not a specification and does not assure specific product characteristics or make reference to the suitability of the product for a specific application. Because Saint-Gobain cannot anticipate or control every application, we strongly recommend testing of this product under individual application conditions. The application, use and conversion of this product are the user's responsibility.

Limited Warranty: For a period of 6 months from the date of first sale, Saint-Gobain Performance Plastics warrants this product(s) to be free from defects in manufacturing. Our only obligation will be to provide replacement product for any portion proving defective, or at our option, to refund the purchase price thereof. User assumes all other risks, if any, including the risk of injury, loss or damage, whether direct or consequential, arising out of the use, misuse or inability to use this product(s).

SAINT-GOBAIN PERFORMANCE PLASTICS DISCLAIMS ANY AND ALL OTHER WARRANTIES, EXPRESSED OR IMPLIED, INCLUDING THE IMPLIED WARRANTIES OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE.

NOTE: Saint-Gobain Performance Plastics Corporation does not assume any responsibility or liability for any advice furnished by it, or for the performance or results of any installation or use of the product(s) or of any final product into which the product(s) may be incorporated by the purchaser and/or user. The purchaser and/or user should perform their own tests to determine the suitability and fitness of the product(s) for the particular purpose desired in any given situation.

2302-351020R-EN-CHREU-RR-1605

©2016 Saint-Gobain Performance Plastics