

Norton® ETFE Fluoropolymer Film



High Yield Fluoropolymer Film

Norton® ETFE fluoropolymer film is manufactured from a copolymer of ethylene and tetrafluoroethylene resin. This material offers the outstanding performance of fluoropolymer film over a temperature range from cryogenic to 165°C (330°F). The resistance to chemicals and weathering, low flammability, and stress crack resistance make this film an excellent candidate for a wide variety of applications.

Weatherable Applications

Norton® ETFE film offers excellent mechanical properties and tear resistance. The high light transmission (> 95%) of Norton® ETFE film, when combined with its excellent mechanical and chemical properties, provides excellent performance in architectural roofing designs and greenhouses. Norton® ETFE film is also an excellent choice in solar collector applications due to its outstanding physical properties and high coverage factor resulting from its low density.

Low Surface-energy Applications

Norton® ETFE film offers a low surface energy, making it an excellent choice for release applications up to 350°F process temperature. The low density of this material, compared to Norton® FEP film, provides greater coverage per pound for composite molding release film applications. The low surface energy of Norton® ETFE can also be utilized in applications such as wall coverings and anti-graffiti protection for high traffic areas.

Fabrication Capabilities

Norton® ETFE film offers processors excellent dimensional stability for secondary processing such as thermoforming and welding. Products utilizing Saint-Gobain's surface treatment technologies, such as C-treatment, improve bondability characteristics for metalizing processes and adhesive coating.

Norton® is a registered trademark.

Features/Benefits

- Superior release properties
- Excellent weatherability
- Performance from -200°C (-328°F) to 165°C (330°F)
- Excellent chemical and mechanical properties
- Thermoformable
- Product thicknesses from 0.0005" (0.0127 mm) to 0.020" (0.5 mm)
- Width up to 62" (1575 mm) for 0.0005" to 0.010" and up to 48" for 0.010"-0.020"
- Blue, red and custom colors available
- Available in cementable (surface treated) form



Excellent performance in architectural roofing designs



ETFE release film yields 19% more per pound than FEP

Norton® ETFE Film — Typical Physical Properties*

Property	ASTM Method	Metric Value	Metric Units	English Value	English Units
General					
Specific Gravity	D-792	1.70-1.76		1.70-1.76	
Yield (1 mil film)		22.5	m ² /kg	110	ft ² /lb
Flammability	UL-94	V-0		V-0	
Water Absorption, 24 hrs		<0.03	%	<0.03	%
Mechanical					
Tensile Strength @ Break	D-882	48	MPa	7000	psi
Elongation @ Break	D-882	300	%	300	%
Tensile Modulus	D-882	965	MPa	140000	psi
Propagating Tear Strength, 1 mil	D-1922	>2.9	N	0.65	lb _f
Electrical					
Dielectric Strength, 1 mil	D-149	215	kV/mm	5500	V/mil
Dielectric Constant, 1 kHz	D-150	2.6		2.6	
Dissipation Factor, 1 kHz	D-150	<0.0008		<0.0008	
Thermal					
Melt Point	D-3418	250-270	°C	482-518	°F
Continuous Service Temperature		165	°C	330	°F
Specific Heat		2000	J/(kg•°K)	0.46	BTU/(lb•°F)
Coefficient of Thermal Conductivity		0.238	W/(m•°K)	1.65	BTU•in/(hr•ft ² •°F)
Limiting Oxygen Index	D-2863	30	%	30	%
Optical					
Refractive Index	D-542	1.40		1.40	

*Represent typical performance properties and should not be used for specification purposes.

Contact your Saint-Gobain Performance Plastics representative for appropriate values.



PERFORMANCE PLASTICS

Saint-Gobain Performance Plastics
Advanced Films and Fabrics—The Americas
150 Dey Road
Wayne, NJ 07470-4699
Phone: (800) 526-7844
Fax: (973) 696-4056

Saint-Gobain Performance Plastics
Advanced Films and Fabrics—Asia
Suite 1203, No. 147
Chienkwo North Road Section 2
Taipei Taiwan, 104
Taiwan
Tel: 886 (2) 25034201
Fax: 886 (2) 25034202

Saint-Gobain Performance Plastics
Advanced Films and Fabrics—Europe
Clonroad
Ennis
County Clare
Ireland
Tel: 353 65 68 20988
Fax: 353 65 68 20993

Limited Warranty: For a period of 6 months from the date of first sale, Saint-Gobain Performance Plastics Corporation warrants this product(s) to be free from defects in manufacturing. Our only obligation will be to provide replacement product for any portion proving defective, or at our option, to refund the purchase price thereof. User assumes all other risks, if any, including the risk of injury, loss or damage, whether direct or consequential, arising out of the use, misuse, or inability to use this product(s). SAINT-GOBAIN PERFORMANCE PLASTICS DISCLAIMS ANY AND ALL OTHER WARRANTIES, EXPRESSED OR IMPLIED, INCLUDING THE IMPLIED WARRANTIES OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE.



NOTE: Saint-Gobain Performance Plastics Corporation does not assume any responsibility or liability for any advice furnished by it, or for the performance or results of any installation or use of the product(s) or of any final product into which the product(s) may be incorporated by the purchaser and/or user. The purchaser and/or user should perform its own tests to determine the suitability and fitness of the product(s) for the particular purpose desired in any given situation.