

# laminates

## DELMAT POLYESTER 68010 GPO-3

- ▶ UL approved, file number E 70284, classified GPO-3 according to NEMA LI 1
- ▶ Flammability UL 94 = V-0 from 0,8mm to 60mm
- ▶ Good mechanical properties at high temperatures
- ▶ Temperature Index 155
- ▶ Halogen free
- ▶ Fire classification acc.to NF F 16-101 : M1 I1 F1
- ▶ Easy to cold punch up to 6mm

### General description

Delmat Polyester 68010 GPO-3 are sheet laminates based on glass mat and polyester resin systems.

### RoHS Directive

Hazardous products listed in the EU-directive 2002/95/CE (ROHS-directive), §4 section 1, are not used as ingredients in this material.

### Application

Switchboards  
LV- and HV circuit breakers  
Phase barriers  
Switchboard bottom plates  
Arc chute chambers panels  
Connection supports  
Protection panels  
Insulation carriers  
Cable clamps  
Bus bars supports  
Power electronics...

### Standards

NEMA LI 1 : GPO-3 for all thicknesses from 0,8 to 60mm  
IEC 60893-3-5 : UP GM 203  
EN 60893-3-5 : UP GM 203  
NF C 26-153 : Vm P2e  
DIN 7735 : Hm 2471

### Form of delivery

Sheet size : 2000 +/-10mm x 1000 +/-10mm  
Thicknesses : 0,8mm to 60mm

The sheets are untrimmed. Homogeneity on a width of 13mm from the edges is not guaranteed.

This product can be delivered in machined parts according to specific drawings.

### Colour

Red, RAL 3003

		Value	Test norm
<b>Physical properties</b>			
Density	g/cm <sup>3</sup>	1.8 ± 0.1	ISO 1183 (method A)
Water absorption after 24h immersion at 23°C, thickness 4mm	mg	<50	ISO 62 (method 1)
Flammability		V-0	UL 94
<b>Mechanical properties</b>			
Flexural strength at 130°C, flatwise	MPa	95	ISO 178
Tensile strength, //, at 23°C	MPa	100	ISO 527
Modulus of elasticity in flexure at 130°C, flatwise	MPa	5000	ISO 178
Flexural strength at 23°C, flatwise	MPa	160	ISO 178
Bonding strength (10mm thick)	N	5000	ASTM D 229
Modulus of elasticity in flexure at 23°C, flatwise	MPa	10000	ISO 178
Compressive strength at 23°C, flatwise	MPa	280	ISO 604
<b>Thermal properties</b>			
Temperature index (TI)		155	IEC 60216
<b>Electrical properties</b>			
Insulation resistance, as received	MOhm	10 <sup>7</sup>	IEC 60167
Comparative tracking index - CTI		600	IEC 60112
Edgewise breakdown voltage, step by step, in oil at 23° C after immersion 48h/50°C/water	kV	20	IEC 60243-1
Relative permittivity at 1 MHz		<4.5	IEC 60250
Arc resistance	s	180	ASTM D 495
Edgewise breakdown voltage, step by step, in oil at 90° C, as received	kV	80	IEC 60243-1
Dissipation factor at 1 MHz		<0.05	IEC 60250
Insulation resistance, after 24h immersion in water at 23°C	MOhm	10 <sup>3</sup>	IEC 60167
Flatwise electric strength, step by step test, in oil at 90°C	kV/mm	12	IEC 60243-1
Tracking and erosion resistance		1 B 2.5	IEC 60587

The product properties set forth in this data sheet are based on the results of testing of typical material produced by the affiliated companies of Von Roll Holding Ltd. (underneath referred as Von Roll). Some variation in product properties is typical. Comments or suggestions relating to any subject other than product properties are offered only to call the end-user's or other person's attention to considerations which may be relevant in the independent determination of the use and/or manner of use of product. Von Roll does not claim or warrant that the use of its product will have the results described in this data sheet or that the information provided is complete, accurate or useful. The user should test the product to determine its properties and its suitability for the intended use. Von Roll expressly disclaims any liability for any damage, harm, injury, cost or expense to any person resulting directly or indirectly from that person's reliance on any information contained in this data sheet. Nothing contained in this data sheet constitutes representation or warranty as to any matter whatsoever. Von Roll makes no warranties whatsoever in this data sheet, expressed or implied, including any implied warranty or fitness for a particular use or purpose. Von Roll shall in no event be liable for incidental, exemplary, punitive or consequential damages.