

laminates

CDM ESD 68940

- ▶ Good performances with lead free soldering process.
- ▶ Increased temperature resistance : good performances at temperatures higher than 300°C.
- ▶ Excellent flux resistance.
- ▶ Dissipative material. Surface resistivity 10E5 to 10E9 Ohm/Square.
- ▶ Optical sensitiveness : grey color enables an easy and improved detection by infra-red cells.
- ▶ Low deformation.
- ▶ Excellent dimensional stability.
- ▶ Improved machinability.

General description

The CDM range of products exhibits higher mechanical and resistance properties as standard composite materials.

The random glass mat substrate present in the CDM ESD 68940 minimizes delaminations problems during machining or pallet use.

The relative low thermal conductivity in the CDM materials allows a rapid pallet turnaround eliminating most of the time both the necessity to provide a cooling station and the process heat sink effect experienced in the metallic pallets.

CDM materials can substitute metallic solder frames (or other materials) with great advantages.

Flux resistance is depending on composition and pH level. Highly acid as well as basic fluxes often require a regular cleaning of remaining powders in order to preserve the stability of CDM material.

Due to the high fiberglass content, machining is recommended with carbide or diamond toolings. Precise machining with very accurate tolerances can be achieved by experts in the conception and machining of pallets.

RoHS Directive

Hazardous products listed in the EU-directive 2002/95/CE (ROHS-directive), §4 section 1, are

		Value	Test norm
Mechanical properties			
Flexural strength at 23°C, flatwise	MPa	350	ISO 178
Flexural strength at 150°C, flatwise	MPa	200	ISO 178
Modulus of elasticity in flexure at 23°C, flatwise	MPa	18000	ISO 178
Modulus of elasticity in flexure at 150°C, flatwise	MPa	12000	ISO 178
Electrical properties			
Surface resistivity	Ohm/square	10E5 to 10E9	IEC 60093
Physical properties			
Density	g/cm ³	1.9 ±0.1	ISO 1183 (method A)
Water absorption 24h 23°C	%	<0.10	ISO 62 (method 1)
Linear coefficient of thermal expansion, parallel	K ⁻¹	10.10 ⁻⁶	VSM 77110
Thermal properties			
Thermal conductivity	W/m.K	0.3	DIN 52612

not used as ingredients in this material.

Application

- Can be used in lead free process
- Full process solder wave, SMT and selective soldering process
- Components insertion
- SMT placement
- Reflow soldering
- Components protection
- Testing of PCBs
- Cleaning of PCB boards

Availability

- Standard sheet size : 2350 +/-10mm x 1335 +/-10mm or 2000 x 1250 mm
- Surface grinded (both sides)
- Standard thicknesses available :
- 3mm, 4mm, 5mm, 6mm, 8mm, 10mm, 12mm

Description

CDM ESD 68940 is a composite material made of glass mat, combined with a high mechanical resistance resin system.
Color : Grey

The product properties set forth in this data sheet are based on the results of testing of typical material produced by the affiliated companies of Von Roll Holding Ltd. (underneath referred as Von Roll). Some variation in product properties is typical. Comments or suggestions relating to any subject other than product properties are offered only to call the end-user's or other person's attention to considerations which may be relevant in the independent determination of the use and/or manner of use of product. Von Roll does not claim or warrant that the use of its product will have the results described in this data sheet or that the information provided is complete, accurate or useful. The user should test the product to determine its properties and its suitability.

for the intended use. Von Roll expressly disclaims any liability for any damage, harm, injury, cost or expense to any person resulting directly or indirectly from that person's reliance on any information contained in this data sheet. Nothing contained in this data sheet constitutes representation or warranty as to any matter whatsoever. Von Roll makes no warranties whatsoever in this data sheet, expressed or implied, including any implied warranty or fitness for a particular use or purpose. Von Roll shall in no event be liable for incidental, exemplary, punitive or consequential damages.

A large, light blue watermark of the word "vonRoll" is positioned at the bottom of the page, spanning most of the width. The "v" is lowercase, and "onRoll" is uppercase.